

Huntsman Araldite RD-2 Reactive Diluent

Category : Polymer , Thermoset , Epoxy , Epoxy Encapsulant, Unreinforced

Material Notes:

Weight per Epoxide (EEW, g/eq) 120 to 135. Max color is 1. Comments/Applications: 1,4 butanediol diglycidyl ether - difunctional epoxy.

Versus RD-1 - gives higher flashpoint (280Â°F vs. 120Â°F); Higher boiling (260Â°C vs. 170Â°C), faint odor, less efficient viscosity reduction. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-RD-2-Reactive-Diluent.php

Physical Properties	Metric	English	Comments
Viscosity	13 - 18 cP	13 - 18 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China