

Huntsman Araldite XB 4383-1 Brominated Resin

Category : Polymer , Thermoset , Epoxy

Material Notes:

Weight per Epoxide (EEW, g/eq) 317 to 345. Max color is 6. Comments/Applications: For use in the manufacturing of thin laminates, prepregs and rigid laminates for printed wiring boards requiring flame retardance. 80% solids in MEK. High performance FR-4 epoxy laminating system. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Araldite-XB-4383-1-Brominated-Resin.php

Physical Properties	Metric	English	Comments
Viscosity	1200 - 2000 cP	1200 - 2000 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China