

Huntsman DY 062 Epoxy Accelerator

Category: Polymer, Thermoset, Epoxy, Epoxy Cure Resin

Material Notes:

Mix Ratio with GY 6010 is 5.Comments/Applications: Reduces gel time and cure schedule for adhesives and other fast cure epoxy systems.

Benzyl dimethyl amine (BDMA)-tertiary amine accelerator. Compatible with anhydride and polyamide hardeners. Flexible mix ratio = 0.5 - 10.0 PHR, with GY 6010.Data provided by Ciba Specialty Chemicals.Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-DY-062-Epoxy-Accelerator.php

Physical Properties	Metric	English	Comments
Viscosity	1.0 - 5.0 cP	1.0 - 5.0 cP	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China