

Huntsman HT 9719-1 Aromatic Amine

Category : Polymer , Thermoset , Epoxy

Material Notes:

Approx. H+ equivalent weight 63. Mix Ratio with GY 6010 is 36. Comments/Applications: 3,3' -diaminodiphenyl sulfone, micropulverized, solid amine. Composites, adhesives. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HT-9719-1-Aromatic-Amine.php

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	165 - 175 Â°C	329 - 347 Â°F	Softening Range

Processing Properties	Metric	English	Comments
Processing Temperature	175 Â°C	347 Â°F	Cure Schedule: 4 hrs. at 175Â°C or 24 hrs at 120Â°C.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China