

## Huntsman HY 283 Cycloaliphatic Amine

Category : Polymer , Thermoset , Epoxy , Epoxy, Cycloaliphatic, Molded

### Material Notes:

Approx. H+ equivalent weight 133. Mix Ratio with GY 6010 is 70. Comments/Applications: Modified polyamidoamine, low viscosity, solvent free. No induction, excellent gloss, chemical resistance. \*Flexible mix ration - 70 to 100 phr, with GY 6010. High solids marine/maintenance primers, floorings, coatings. EPA potable water. Mil spec. 24441. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-HY-283-Cycloaliphatic-Amine.php](http://www.lookpolymers.com/polymer_Huntsman-HY-283-Cycloaliphatic-Amine.php)

Physical Properties	Metric	English	Comments
Viscosity	2700 - 6400 cP	2700 - 6400 cP	

Processing Properties	Metric	English	Comments
Pot Life	150 min	150 min	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China