

Huntsman HY 3441 Phenalkamine Hardener

Category : Polymer , Thermoset , Epoxy , Epoxy Cure Resin

Material Notes:

Approx. H+ equivalent weight 130. Mix Ratio with GY 6010 is 40. Comments/Applications: Low temperature cure coatings with excellent corrosion and moisture resistance. Cure can go down to 0°C. For use in maintenance and marine coatings. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HY-3441-Phenalkamine-Hardener.php

Processing Properties	Metric	English	Comments
Processing Temperature	25.0 °C	77.0 °F	Cure Schedule: 7 days @ 25°C

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China