

Huntsman HY 5200 Aromatic Amine

Category : Polymer , Thermoset , Epoxy

Material Notes:

Approx. H+ equivalent weight 45. Mix Ratio with GY 6010 is 23. Comments/Applications: Liquid aromatic amine. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HY-5200-Aromatic-Amine.php

Physical Properties	Metric	English	Comments
Viscosity	50 - 350 cP	50 - 350 cP	

Processing Properties	Metric	English	Comments
Processing Temperature	80.0 Å°C	176 Å°F	Cure Schedule: 2 hrs @ 80Å°C or 2 hrs @ 150Å°C
Pot Life	480 min	480 min	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China