

Huntsman HY 815 US Polyamide

Category: Polymer, Thermoset, Epoxy

Material Notes:

Approx. H+ equivalent weight 150. Mix Ratio with GY 6010 is 81. Comments/Applications: Solvent free, high molecular weight, low amine content. Superior adhesion, easily pigmented. Trade sale paint enamels. Industrial maintenance, FDA. Flexible mix ratio. Usually used with "Type 1" epoxy resins. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-HY-815-US-Polyamide.php

Physical Properties	Metric	English	Comments
Viscosity	50000 - 75000 cP	50000 - 75000 cP	

Processing Properties	Metric	English	Comments
Pot Life	600 min	600 min	

Contact Songhan Plastic Technology Co.,Ltd.

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China