

Huntsman Kerimid 701 A US Resin

Category : Polymer , Thermoset , Epoxy

Material Notes:

Comments/Applications: Used with Kerimid 701-1 B US for high Tg laminate systems. Suggested ratio 3 parts A to 1 part B. Data provided by Ciba Specialty Chemicals. Ciba Specialty Chemicals has been acquired by Huntsman.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Kerimid-701-A-US-Resin.php

Physical Properties	Metric	English	Comments
Viscosity	2000 - 8000 cP	2000 - 8000 cP	

Processing Properties	Metric	English	Comments
Processing Temperature	171 Â°C	340 Â°F	Gel time is 200-400 min. at 171Â°C.

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China