

## Huntsman PE2038 Injection Molding Polyethylene (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

### Material Notes:

Homopolymer and FDA compliant. Features: High mechanical flexing properties, excellent processability, good stress crack resistance, and very good low temperature strength. Applications: Injection molding: industrial parts, electrical components, shoe parts, housewares, and hinged closures. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170. Information provided by Huntsman Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-PE2038-Injection-Molding-Polyethylene-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Huntsman-PE2038-Injection-Molding-Polyethylene-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	9.0 g/10 min	9.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	44	44	ASTM D2240
Tensile Strength, Ultimate	10.0 MPa	1450 psi	ASTM D638
Tensile Strength, Yield	9.00 MPa	1310 psi	ASTM D638
Elongation at Break	475 %	475 %	ASTM D638
Modulus of Elasticity	0.169 GPa	24.5 ksi	Secant; ASTM D638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	85.0 °C	185 °F	ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China