

## Huntsman PE2067 Injection Molding Polyethylene (discontinued \*\*)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

### Material Notes:

Homopolymer and FDA compliant. Features: High flow resin, provides excellent gloss and surface characteristics, and minimum cycle time. Applications: Injection molding: lids. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170. Information provided by Huntsman Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Huntsman-PE2067-Injection-Molding-Polyethylene-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_Huntsman-PE2067-Injection-Molding-Polyethylene-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	0.924 g/cc	0.0334 lb/in <sup>3</sup>	ASTM D1505
Melt Flow	35 g/10 min	35 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	55	55	ASTM D2240
Tensile Strength, Ultimate	10.0 MPa	1450 psi	ASTM D638
Tensile Strength, Yield	13.0 MPa	1890 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Modulus of Elasticity	0.345 GPa	50.0 ksi	Secant; ASTM D638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	98.0 °C	208 °F	ASTM D1525

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China