

Huntsman PE2075 Injection Molding Polyethylene (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Molded

Material Notes:

Homopolymer and FDA compliant. Features: Very high flow rapid set-up characteristics, excellent clarity, and gloss. Applications: Injection molding: lids and difficult to fill applications. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170 Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE2075-Injection-Molding-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.924 g/cc	0.0334 lb/in ³	ASTM D1505
Melt Flow	70 g/10 min	70 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	54	54	ASTM D2240
Tensile Strength, Ultimate	9.00 MPa	1310 psi	ASTM D638
Tensile Strength, Yield	12.0 MPa	1740 psi	ASTM D638
Elongation at Break	100 %	100 %	ASTM D638
Modulus of Elasticity	0.345 GPa	50.0 ksi	Secant; ASTM D638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	97.0 °C	207 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China