

Huntsman PE5080 Extrusion Coating Polyethylene (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Extrusion Grade

Material Notes:

Homopolymer and FDA compliant. Features: Excellent draw down, low neck-in, and excellent adhesion. Applications: Extrusion: coating grade and thin coatings. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170. Film properties based on 1.0 guage (25 µm) thickness; blow-up ratio 2:1. Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE5080-Extrusion-Coating-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in ³	ASTM D1505
Melt Flow	12 g/10 min	12 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	45	45	ASTM D2240
Tensile Strength, Ultimate	10.0 MPa	1450 psi	ASTM D638
Tensile Strength, Yield	9.00 MPa	1310 psi	ASTM D638
Film Elongation at Break, MD	190 %	190 %	ASTM D882
Film Elongation at Break, TD	280 %	280 %	ASTM D882
Elongation at Break	500 %	500 %	ASTM D638
Modulus of Elasticity	0.166 GPa	24.1 ksi	Secant; ASTM D638
Secant Modulus, MD	0.0970 GPa	14.1 ksi	ASTM D882
Secant Modulus, TD	0.145 GPa	21.0 ksi	ASTM D882
Film Tensile Strength at Break, MD	14.0 MPa	2030 psi	ASTM D882
Film Tensile Strength at Break, TD	10.0 MPa	1450 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	86.0 °C	187 °F	ASTM D1525

Processing Properties	Metric	English	Comments
Melt Temperature	249 - 288 °C	480 - 550 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China