

Huntsman PE8020 Specialty Polyethylene (discontinued **)

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LDPE , Low Density Polyethylene (LDPE), Film Grade

Material Notes:

Homopolymer and FDA compliant. Features: Yields film with excellent draw down and machinability. Applications: Film extrusion: gel free film applications. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)2.2 under condition of use B through H described in Table 2 of 21 CFR 176.170. Film properties based on 1.0 guage (25 µm) thickness; blow-up ratio 2:1. Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-PE8020-Specialty-Polyethylene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.922 g/cc	0.0333 lb/in ³	ASTM D1505
Melt Flow	6.5 g/10 min	6.5 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	48	48	ASTM D2240
Tensile Strength, Ultimate	11.0 MPa	1600 psi	ASTM D638
Tensile Strength, Yield	11.0 MPa	1600 psi	ASTM D638
Film Elongation at Break, MD	320 %	320 %	ASTM D882
Film Elongation at Break, TD	380 %	380 %	ASTM D882
Elongation at Break	400 %	400 %	ASTM D638
Modulus of Elasticity	0.297 GPa	43.1 ksi	Secant; ASTM D638
Secant Modulus, MD	0.204 GPa	29.6 ksi	ASTM D882
Secant Modulus, TD	0.255 GPa	37.0 ksi	ASTM D882
Dart Drop Test	50.0 g	0.110 lb	ASTM D1709
Film Tensile Strength at Break, MD	14.0 MPa	2030 psi	ASTM D882
Film Tensile Strength at Break, TD	16.0 MPa	2320 psi	ASTM D882

Thermal Properties	Metric	English	Comments
Vicat Softening Point	92.0 °C	198 °F	ASTM D1525

Optical Properties	Metric	English	Comments
Gloss	49 %	49 %	at 45°; ASTM D523

Processing Properties	Metric	English	Comments
Melt Temperature	150 - 160 °C	302 - 320 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China