

Huntsman Rexell® L2101 Injection Molding LLDPE (discontinued **)

Category : Polymer , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE), Injection Molded

Material Notes:

Linear-low very low density copolymer, injection molding, FDA compliant. Features: High flow, flexible with excellent environmental stress crack (ESCR), and warpage resistance. Applications: Fitments, large lids, and containers requiring low warpage. FDA Notes: Conforms to FDA regulation 21 CFR 177.1520 (c)3.1. Information provided by Huntsman Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Huntsman-Rexell-L2101-Injection-Molding-LLDPE-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.918 g/cc	0.0332 lb/in ³	ASTM D1505
Viscosity	48 cP	48 cP	Apparent viscosity; ASTM D3835
	@Shear Rate 5000 1/s, Temperature 230 °C	@Shear Rate 5000 1/s, Temperature 446 °F	
	92 cP	92 cP	
	@Shear Rate 1000 1/s, Temperature 230 °C	@Shear Rate 1000 1/s, Temperature 446 °F	Apparent viscosity; ASTM D3835
	135 cP	135 cP	Apparent viscosity; ASTM D3835
	@Shear Rate 300 1/s, Temperature 230 °C	@Shear Rate 300 1/s, Temperature 446 °F	
Melt Flow	24 g/10 min	24 g/10 min	Melt Flow Ratio (I10/I2) is 7.3; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	52	52	ASTM D2240
Tensile Strength, Yield	9.00 MPa	1310 psi	ASTM D638
Elongation at Break	>= 300 %	>= 300 %	ASTM D638
Modulus of Elasticity	0.248 GPa	36.0 ksi	ASTM D638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	86.0 °C	187 °F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China