

Hydrogenated Nitrile Rubber (HNBR)

Category : Polymer , Thermoset , Rubber or Thermoset Elastomer (TSE)

Material Notes:

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hydrogenated-Nitrile-Rubber-HNBR.php

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	40 - 100	40 - 100	Depends on compounding
Tensile Strength, Ultimate	15.0 - 30.0 MPa	2180 - 4350 psi	
Elongation at Break	100 - 400 %	100 - 400 %	

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	150 °C	302 °F	
Minimum Service Temperature, Air	-25.0 °C	-13.0 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China