

Hyosung Topilene B240T PP

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

B240T Extrusion Impact Copolymer Applications: Thermoforming sheet Stationary sheet Characteristics: High impact High stiffness Information provided by Hyosung Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hyosung-Topilene-B240T-PP.php

Physical Properties	Metric	English	Comments
Melt Flow	0.50 g/10 min	0.50 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	70	70	ASTM D785
Tensile Strength, Yield	29.4 MPa	4270 psi	ASTM D638
Elongation at Break	500 %	500 %	ASTM D638
Flexural Modulus	1.32 GPa	192 ksi	ASTM D790
Izod Impact, Unnotched	NB	NB	ASTM D256
	0.637 J/cm @Temperature -10.0 Â°C	1.19 ft-lb/in @Temperature 14.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 Â°C	230 Â°F	ASTM D648
Vicat Softening Point	150 Â°C	302 Â°F	ASTM D1525

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China