

Hyosung Topilene C600ME PP

Category : Polymer , Thermoplastic , Polypropylene (PP)

Material Notes:

C600ME Butene Random Copolymer
Applications: Film
Characteristics: Excellent transparency & gloss
Low sealing temperature
High hot-tack strength
Good stiffness
Information provided by Hyosung Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hyosung-Topilene-C600ME-PP.php

Physical Properties	Metric	English	Comments
Melt Flow	7.0 g/10 min	7.0 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	26.5 MPa	3840 psi	ASTM D638
Elongation at Break	>= 500 %	>= 500 %	ASTM D638
Flexural Modulus	0.785 GPa	114 ksi	ASTM D790
Izod Impact, Unnotched	0.637 J/cm	1.19 ft-lb/in	ASTM D256

Thermal Properties	Metric	English	Comments
Melting Point	133 Â°C	271 Â°F	

Descriptive Properties	Value	Comments
Additives	AB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China