

Hyosung Topilene J640A PP

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

J640A Injection Impact Copolymer Applications: Large articles:Washing M/C partsElectric applianceIndustrial appliance
 Characteristics:Medium impactFlowabilityInformation provided by Hyosung Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Hyosung-Topilene-J640A-PP.php

Physical Properties	Metric	English	Comments
Melt Flow	18 g/10 min	18 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	80	80	ASTM D785
Tensile Strength, Yield	27.5 MPa	3980 psi	ASTM D638
Elongation at Break	400 %	400 %	ASTM D638
Flexural Modulus	1.23 GPa	178 ksi	ASTM D790
Izod Impact, Unnotched	0.932 J/cm	1.74 ft-lb/in	ASTM D256
	0.441 J/cm @Temperature -10.0 Â°C	0.827 ft-lb/in @Temperature 14.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	105 Â°C	221 Â°F	ASTM D648
Vicat Softening Point	150 Â°C	302 Â°F	ASTM D1525
Flammability, UL94	HB	HB	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.comEmail : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China