

## Hyosung Topilene J740 PP

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

### Material Notes:

J740 Injection Impact Copolymer Applications: Large articles:Washing M/C parts Electric appliance Industrial  
appliance Characteristics: Medium impact Flowability Information provided by Hyosung Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hyosung-Topilene-J740-PP.php](http://www.lookpolymers.com/polymer_Hyosung-Topilene-J740-PP.php)

Physical Properties	Metric	English	Comments
Melt Flow	25 g/10 min	25 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	80	80	ASTM D785
Tensile Strength, Yield	27.5 MPa	3980 psi	ASTM D638
Elongation at Break	400 %	400 %	ASTM D638
Flexural Modulus	1.27 GPa	185 ksi	ASTM D790
Izod Impact, Unnotched	0.785 J/cm	1.47 ft-lb/in	ASTM D256
	0.392 J/cm @Temperature -10.0 Â°C	0.735 ft-lb/in @Temperature 14.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 Â°C	230 Â°F	ASTM D648
Vicat Softening Point	150 Â°C	302 Â°F	ASTM D1525
Flammability, UL94	HB	HB	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China