

## Hyosung Topilene J742S PP

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Impact Modified; Molded/Extruded

**Material Notes:**

J742S Injection Impact Copolymer Applications: Large articles:Washing M/C partsElectric applianceIndustrial appliance  
 Characteristics:Medium impactHigh stiffnessInformation provided by Hyosung Corporation

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Hyosung-Topilene-J742S-PP.php](http://www.lookpolymers.com/polymer_Hyosung-Topilene-J742S-PP.php)

Physical Properties	Metric	English	Comments
Melt Flow	28 g/10 min	28 g/10 min	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	85	85	ASTM D785
Tensile Strength, Yield	28.4 MPa	4120 psi	ASTM D638
Elongation at Break	200 %	200 %	ASTM D638
Flexural Modulus	1.47 GPa	213 ksi	ASTM D790
Izod Impact, Unnotched	0.785 J/cm	1.47 ft-lb/in	ASTM D256
	0.441 J/cm @Temperature -10.0 Â°C	0.827 ft-lb/in @Temperature 14.0 Â°F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	120 Â°C	248 Â°F	ASTM D648
Vicat Softening Point	150 Â°C	302 Â°F	ASTM D1525
Flammability, UL94	HB	HB	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China