

ICO Polymers ICORENE[®],ç 110-3561 LMDPE Rotational Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE , Linear Medium Density Polyethylene (LMDPE), Rotational Molded

Material Notes:

Description: ICORENE 110-3561 is a linear medium density polyethylene developed for use in rotational molding. This is a very fast processing material that quickly molds out to offer low surface porosity and good overall properties. Key Characteristics: fast processing, low pinholing, wide processing window. Applications: This ICORENE[®] grade is particularly suitable for use in toy applications. Information provided by ICO Polymers.A Schulman acquired ICO, Inc. in 2010.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ICO-Polymers-ICORENE-110-3561-LMDPE-Rotational-Molding-Resin.php

Physical Properties	Metric	English	Comments
Density	0.934 g/cc	0.0337 lb/in ³	ASTM D1505
Melt Index of Compound	6.0 g/10 min @Load 2.16 kg, Temperature 190 °C	6.0 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	55	55	ASTM D2240
Tensile Strength, Yield	18.0 MPa	2610 psi	50 mm/min; ASTM D638
Elongation at Break	500 %	500 %	50 mm/min; ASTM D638
Flexural Modulus	0.700 GPa	102 ksi	1.3 mm/min; ASTM D790

Descriptive Properties	Value	Comments
UV Light Weatherometer Test	8000 hours	ASTM G26

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China