

## ICO Polymers ICORENE<sup>®</sup> 115-1325 LMDPE Rotational Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE , Linear Medium Density Polyethylene (LMDPE), Rotational Molded

**Material Notes:**

Description: ICORENE 115-1325 is a linear medium density polyethylene developed for use in rotational molding. It is an easy processing material with good surface gloss, scratch resistance and generally balanced physical properties. Key Characteristics: easy processing, good rigidity, good scratch resistance. Applications: This ICORENE<sup>®</sup> grade is particularly suitable for use in playground applications.

Information provided by ICO Polymers. A Schulman acquired ICO, Inc. in 2010.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ICO-Polymers-ICORENE-115-1325-LMDPE-Rotational-Molding-Resin.php](http://www.lookpolymers.com/polymer_ICO-Polymers-ICORENE-115-1325-LMDPE-Rotational-Molding-Resin.php)

Physical Properties	Metric	English	Comments
Density	0.936 g/cc	0.0338 lb/in <sup>3</sup>	ASTM D1505
Melt Index of Compound	4.2 g/10 min @Load 2.16 kg, Temperature 190 °C	4.2 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	55	55	ASTM D2240
Tensile Strength, Yield	19.0 MPa	2760 psi	50 mm/min; ASTM D638
Elongation at Break	900 %	900 %	50 mm/min; ASTM D638
Flexural Modulus	0.690 GPa	100 ksi	1.3 mm/min; ASTM D790
Impact	19 @Temperature -20.0 °C	19 @Temperature -4.00 °F	J/mm, instrumented impact, rotomolded test sample; ICO R&D1.14

Descriptive Properties	Value	Comments
UV Light Weatherometer Test	8000 hours	ASTM G26

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China