

ICO Polymers ICORENE[®],ç 155-1331 LMDPE Rotational Molding Resin

Category : Polymer , Thermoplastic , Polyethylene (PE) , MDPE , Linear Medium Density Polyethylene (LMDPE), Rotational Molded

Material Notes:

Description: ICORENE 155-1331 is a linear medium density polyethylene developed for use in rotational molding. It has a great combination of stiffness and toughness in a resin that is easy processing. Key Characteristics: good stiffness, good toughness, low warpage.

Applications: This ICORENE[®] grade is particularly suitable for use in boat applications. Information provided by ICO Polymers.A Schulman acquired ICO, Inc. in 2010.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ICO-Polymers-ICORENE-155-1331-LMDPE-Rotational-Molding-Resin.php

Physical Properties	Metric	English	Comments
Density	0.940 g/cc	0.0340 lb/in ³	ASTM D1505
Melt Index of Compound	3.6 g/10 min @Load 2.16 kg, Temperature 190 °C	3.6 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	62	62	ASTM D2240
Tensile Strength, Yield	18.0 MPa	2610 psi	50 mm/min; ASTM D638
Elongation at Break	500 %	500 %	50 mm/min; ASTM D638
Flexural Modulus	0.75780 GPa	109.91 ksi	1.33 mm/min; ASTM D790
Impact	19 @Temperature -20.0 °C	19 @Temperature -4.00 °F	J/mm, instrumented impact, rotomolded test sample; ICO R&D1.14

Descriptive Properties	Value	Comments
UV Light Weatherometer Test	8000 hours	ASTM G26

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China