

## IRPC Polimaxx Polene 2564PCX TA6 Polypropylene Compound

Category : Polymer , Thermoplastic , Polypropylene (PP)

**Material Notes:**

CHARACTERISTICS: POLYPROPYLENE BLOCK COPOLYMER WITH 30% TALCUM REINFORCED HIGH IMPACT STRENGTH CONTAIN UV STABILIZER AND LONG TERM HEAT AGING ADDITIVES APPLICATIONS: INJECTION MOLDING FOR AUTOPARTS, ELECTRICAL APPLIANCES

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_IRPC-Polimaxx-Polene-2564PCX-TA6-Polypropylene-Compound.php](http://www.lookpolymers.com/polymer_IRPC-Polimaxx-Polene-2564PCX-TA6-Polypropylene-Compound.php)

Physical Properties	Metric	English	Comments
Density	1.14 g/cc	0.0412 lb/in <sup>3</sup>	ASTM D792
Melt Flow	13 g/10 min @Load 2.16 kg, Temperature 230 °C	13 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	88	88	ASTM D785
Tensile Strength, Yield	25.0 MPa	3630 psi	ASTM D638
Elongation at Break	8.0 %	8.0 %	ASTM D638
Flexural Yield Strength	38.2 MPa	5550 psi	ASTM D790
Flexural Modulus	3.40 GPa	493 ksi	ASTM D790
Izod Impact, Notched	0.490 J/cm @Temperature 23.0 °C	0.918 ft-lb/in @Temperature 73.4 °F	ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	140 °C	284 °F	ASTM D648

### Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China