

ITW Devcon Flexane[®] Rubber Repair / Castable Urethane Belt Repair Kit, Black

Category : Polymer , Adhesive , Thermoset , Polyurethane, TS

Material Notes:

Information provided by ITW Devcon

Order this product through the following link:

http://www.lookpolymers.com/polymer_ITW-Devcon-Flexane-Rubber-Repair-Castable-Urethane-Belt-Repair-Kit-Black.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	87	87	Cured; ASTM D2240
Tensile Strength at Break	11.7 MPa	1700 psi	ASTM D412
Elongation at Break	<= 300 %	<= 300 %	ASTM D412
Tear Strength	49.1 kN/m	280 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	300	300	H-18 wheel (1000 gram load)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	48.9 Å°C	120 Å°F	wet
	82.2 Å°C	180 Å°F	dry
Shrinkage	0.14 %	0.14 %	Cured; ASTM D2566

Electrical Properties	Metric	English	Comments
Dielectric Strength	13.8 kV/mm	350 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	720 min	12.0 hour	Functional cure
Pot Life	25.0 min	25.0 min	
	@Temperature 23.9 Å°C	@Temperature 75.0 Å°F	

Descriptive Properties	Value	Comments
Coverage per pound, in ² @ 1/4" thickness	94	
Mix ratio by weight (Resin:Hardener)	72:28	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China