

ITW Devcon Rubber Repair / Castable Urethane Edge & Seal (T-35), Black

Category : Polymer , Adhesive , Thermoset , Polyurethane, TS

Material Notes:

Information provided by ITW Devcon

Order this product through the following link:

http://www.lookpolymers.com/polymer_ITW-Devcon-Rubber-Repair-Castable-Urethane-Edge-Seal-T-35-Black.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0377 lb/in ³	
Viscosity	5000 cP	5000 cP	Mixed Viscosity

Mechanical Properties	Metric	English	Comments
Hardness, Shore A	94	94	Cured; ASTM D2240
Tensile Strength at Break	22.8 MPa	3300 psi	ASTM D412
Elongation at Break	<= 450 %	<= 450 %	ASTM D412
Tear Strength	75.4 kN/m	430 pli	ASTM D624
Taber Abrasion, mg/1000 Cycles	250	250	H-18 wheel (1000 gram load)

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	48.9 Â°C	120 Â°F	wet
	82.2 Â°C	180 Â°F	dry
Shrinkage	0.14 %	0.14 %	Cured; ASTM D2566

Electrical Properties	Metric	English	Comments
Dielectric Strength	13.8 kV/mm	350 kV/in	ASTM D149

Processing Properties	Metric	English	Comments
Cure Time	90.0 min	1.50 hour	Functional cure
Pot Life	3.00 min @Temperature 23.9 Â°C	3.00 min @Temperature 75.0 Â°F	

Descriptive Properties	Value	Comments
Coverage per pound, in ² @ 1/4" thickness	106	

Descriptive Properties	Value	Comments
Mix ratio by weight (Resin:Hardener)	80:20	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China