

Imerys Barnet,ç Kaolin

Category : Ceramic , Clay , Kaolin Clay , Oxide , Aluminum Oxide , Silicon Oxide

Material Notes:

Information provided by Imerys

Order this product through the following link:

http://www.lookpolymers.com/polymer_Imerys-Barnet-Kaolin.php

Physical Properties	Metric	English	Comments
Specific Gravity	2.60 g/cc	2.60 g/cc	
Particle Size	0.30 Åµm	0.30 Åµm	median
	0.50 Åµm	0.50 Åµm	71.5% finer than
	1.0 Åµm	1.0 Åµm	86% finer than
	2.0 Åµm	2.0 Åµm	92% finer than
	5.0 Åµm	5.0 Åµm	98% finer than
	10 Åµm	10 Åµm	98.5% finer than
	20 Åµm	20 Åµm	99.5% finer than
Particle Mesh Size	325 Mesh	325 Mesh	2% retained
pH	>= 4.0	>= 4.0	

Component Elements Properties	Metric	English	Comments
Al2O3	38.5 %	38.5 %	
CaO	0.10 %	0.10 %	
Fe2O3	1.2 %	1.2 %	
K2O	0.20 %	0.20 %	
Loss on Ignition(%)	13.6 %	13.6 %	
MgO	0.050 %	0.050 %	
Na2O	0.10 %	0.10 %	
SiO2	44.8 %	44.8 %	
TiO2	1.45 %	1.45 %	

Processing Properties	Metric	English	Comments
Moisture Content	1.0 - 3.0 %	1.0 - 3.0 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China