

Indium Corp. Indalloy 130 Tin-Lead Solder Alloy

Category : Metal , Nonferrous Metal , Lead Alloy , Solder/Braze Alloy

Material Notes:

Inexpensive utility solder
Information Provided by Indium Corporation

Order this product through the following link:

http://www.lookpolymers.com/polymer_Indium-Corp-Indalloy-130-Tin-Lead-Solder-Alloy.php

Physical Properties	Metric	English	Comments
Density	9.28 g/cc	0.335 lb/in ³	

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	12	12	
Tensile Strength at Break	37.2 MPa	5400 psi	
Elongation at Break	25 %	25 %	
Modulus of Elasticity	23.0 GPa	3340 ksi	
Shear Strength	31.7 MPa	4600 psi	

Thermal Properties	Metric	English	Comments
CTE, linear	25.0 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$	13.9 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$	
	@Temperature 20.0 $\text{Å}^\circ\text{C}$	@Temperature 68.0 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	44.0 W/m-K	305 BTU-in/hr-ft ² - $\text{Å}^\circ\text{F}$	
	@Temperature 85.0 $\text{Å}^\circ\text{C}$	@Temperature 185 $\text{Å}^\circ\text{F}$	
Melting Point	183 - 238 $\text{Å}^\circ\text{C}$	361 - 460 $\text{Å}^\circ\text{F}$	
Solidus	183 $\text{Å}^\circ\text{C}$	361 $\text{Å}^\circ\text{F}$	
Liquidus	238 $\text{Å}^\circ\text{C}$	460 $\text{Å}^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Lead, Pb	60 %	60 %	
Tin, Sn	40 %	40 %	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	0.0000170 ohm-cm	0.0000170 ohm-cm	

Electrical Properties

Metric

English

Comments

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China