

Industeel CLC 1.2738 Prehardened Mold Steel (300HB/30HRC) for Thick Sections

Category : Metal , Ferrous Metal , Carbon Steel , High Carbon Steel , Tool Steel , Mold Steel

Material Notes:

Description: CLC 1.2738 is a 300HB (30HRC) pre-hardened grade specially designed for plastic mold industry. Chromium, Molybdenum, Nickel carbon and manganese additions are optimized to have a fully martensite-bainite microstructure after quenching. The high nickel content (1%) is specially adapted to ensure a perfect homogeneity of structure and hardness through thickness even for very thick blocks (up to 700mm/28"). The steel is melted in electrical furnace and refined with VOD or DH device The cleanliness of the steel is guaranteed as well as the soundness. This makes the steel particularly well adapted for mold even when polishing or chemical etching are required for surface finish quality. Information provided by manufacturer.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Industeel-CLC-12738-Prehardened-Mold-Steel-300HB30HRC-for-Thick-Sections.php

Mechanical Properties	Metric	English	Comments
Hardness, Brinell	300	300	Typical, in Transverse Direction
Tensile Strength, Ultimate	993 MPa	144000 psi	Typical, Transverse Direction
Tensile Strength, Yield	826 MPa @Strain 0.200 %	120000 psi @Strain 0.200 %	Typical, Transverse Direction
Elongation at Break	17 %	17 %	Typical, EL 5.65 Transverse Direction
Modulus of Elasticity	205 GPa	29700 ksi	Typical, in Transverse Direction
Charpy Impact	22.0 J	16.2 ft-lb	Typical (Transverse)

Thermal Properties	Metric	English	Comments
CTE, linear	12.7 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 - 200 $\text{Å}^\circ\text{C}$	7.06 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 - 392 $\text{Å}^\circ\text{F}$	
Thermal Conductivity	29.0 W/m-K @Temperature 20.0 $\text{Å}^\circ\text{C}$	201 BTU-in/hr-ft $\text{Å}^2\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 $\text{Å}^\circ\text{F}$	

Component Elements Properties	Metric	English	Comments
Carbon, C	0.40 %	0.40 %	
Chromium, Cr	1.9 %	1.9 %	
Iron, Fe	94.683 - 94.7 %	94.683 - 94.7 %	As remainder
Manganese, Mn			

Component Elements Properties	Metric	English	Comments
Molybdenum, Mo	0.20 %	0.20 %	
Nickel, Ni	1.0 %	1.0 %	
Phosphorous, P	<= 0.012 %	<= 0.012 %	
Silicon, Si	0.30 %	0.30 %	
Sulfur, S	<= 0.0050 %	<= 0.0050 %	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China