

## Ineos ABS Lustran® 228 Specialty, High Productivity (discontinued \*\*)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

### Material Notes:

Information provided by Bayer Corporation, Plastics Division LANXESS was spun-off from Bayer in early 2005. Business renamed Ineos ABS after INEOS acquires a majority shareholding under a JV with Lanxess in 2007. Subsequently Ineos acquired 100% of Ineos ABS. This product is no longer listed as a standard NAFTA product.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ineos-ABS-Lustran-228-Specialty-High-Productivity-nbspdiscontinued-.php](http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-228-Specialty-High-Productivity-nbspdiscontinued-.php)

Physical Properties	Metric	English	Comments
Density	1.08 g/cc	0.0390 lb/in <sup>3</sup>	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	40 g/10 min @Load 10.0 kg, Temperature 220 °C	40 g/10 min @Load 22.0 lb, Temperature 428 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	40.0 MPa	5800 psi	ASTM D638
Tensile Modulus	2.30 GPa	334 ksi	ASTM D638
Flexural Yield Strength	63.1 MPa	9150 psi	ASTM D790
Flexural Modulus	2.30 GPa	334 ksi	ASTM D790
Izod Impact, Notched	2.20 J/cm @Thickness 3.17 mm	4.12 ft-lb/in @Thickness 0.125 in	ASTM D256

Thermal Properties	Metric	English	Comments
UL RTI, Electrical	60.0 °C @Thickness 1.60 mm	140 °F @Thickness 0.0630 in	UL746B
UL RTI, Mechanical with Impact	60.0 °C @Thickness 1.60 mm	140 °F @Thickness 0.0630 in	UL746B
UL RTI, Mechanical without Impact	60.0 °C @Thickness 1.60 mm	140 °F @Thickness 0.0630 in	UL746B
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	

Thermal Properties	<sup>HB</sup> Metric	<sup>HB</sup> English	Comments
	@Thickness 1.50 mm	@Thickness 0.0591 in	

Optical Properties	Metric	English	Comments
Transmission, Visible	0.00 %	0.00 %	Opaque only

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China