

Ineos ABS Lustran® 248

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Key Features: Unfilled Suitable processing methods: Injection molding

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-248.php

Physical Properties	Metric	English	Comments
Density	1.03 g/cc	0.0372 lb/in ³	
Melt Flow	17 g/10 min @Load 10.0 kg, Temperature 220 °C	17 g/10 min @Load 22.0 lb, Temperature 428 °F	cm ³ /10 min.

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	48.3 MPa	7010 psi	
Elongation at Break	25 %	25 %	Nominal
Elongation at Yield	3.6 %	3.6 %	
Tensile Modulus	2.49 GPa	361 ksi	
Charpy Impact Unnotched	8.70 J/cm ² @Temperature -30.0 °C	41.4 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	2.40 J/cm ² @Temperature -30.0 °C	11.4 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	81.0 µm/m-°C @Temperature 20.0 °C	45.0 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	95.0 °C	203 °F	
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	
Flammability, UL94	HB @Thickness 1.50 mm	HB @Thickness 0.0591 in	UL Recognized

Thermal Properties	Metric	English	Comments
	@Thickness 3.00 mm	@Thickness 0.118 in	UL Recognized

Processing Properties	Metric	English	Comments
Melt Temperature	250 Â°C	482 Â°F	Injection Molding
Mold Temperature	60.0 Â°C	140 Â°F	Injection Molding
Injection Velocity	200 mm/sec	7.87 in/sec	
Injection Pressure	55.0 MPa	7980 psi	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China