

Ineos ABS Lustran® 2863 (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Special grade for smart cards. Information provided by Bayer. LANXESS was spun-off from Bayer in early 2005. Business renamed Ineos ABS after INEOS acquires a majority shareholding under a JV with Lanxess in 2007. Subsequently Ineos acquired 100% of Ineos ABS.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-2863-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	
Melt Flow	13 g/10 min	13 g/10 min	
	@Load 10.0 kg, Temperature 220 °C	@Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	44.0 MPa	6380 psi	
Elongation at Yield	2.0 %	2.0 %	
Tensile Modulus	2.10 GPa	305 ksi	
Charpy Impact Unnotched	0.800 J/cm ²	3.81 ft-lb/in ²	
	@Temperature -30.0 °C	@Temperature -22.0 °F	
Charpy Impact, Notched	2.60 J/cm ²	12.4 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	90.0 µm/m-°C	50.0 µin/in-°F	
	@Temperature 20.0 °C	@Temperature 68.0 °F	
Vicat Softening Point	97.0 °C	207 °F	
Flammability, UL94	HB	HB	
	@Thickness 1.60 mm	@Thickness 0.0630 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+14 ohm-cm	1.00e+14 ohm-cm	
Surface Resistance	1.00e+14 ohm	1.00e+14 ohm	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China