

Ineos ABS Lustran® M203FC

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Molded

Material Notes:

Standard impact strength, easy flowing, high gloss, BgVV and FDA quality for food contact. ,Property data per ISO test methods.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-Lustran-M203FC.php

Physical Properties	Metric	English	Comments
Density	1.05 g/cc	0.0379 lb/in ³	
Melt Flow	33 g/10 min @Load 10.0 kg, Temperature 220 °C	33 g/10 min @Load 22.0 lb, Temperature 428 °F	Estimated using room temperature density

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	46.0 MPa	6670 psi	
Elongation at Yield	2.6 %	2.6 %	
Tensile Modulus	2.40 GPa	348 ksi	
Charpy Impact Unnotched	11.0 J/cm ²	52.4 ft-lb/in ²	
	9.00 J/cm ² @Temperature -30.0 °C	42.8 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	1.50 J/cm ²	7.14 ft-lb/in ²	
	0.700 J/cm ² @Temperature -30.0 °C	3.33 ft-lb/in ² @Temperature -22.0 °F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	0.900 µm/m-°C @Temperature 20.0 °C	0.500 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	98.0 °C	208 °F	
Deflection Temperature at 1.8 MPa (264 psi)	94.0 °C	201 °F	
Vicat Softening Point	99.0 °C	210 °F	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	$\geq 1.00 \times 10^{15}$ ohm-cm	$\geq 1.00 \times 10^{15}$ ohm-cm	
Surface Resistance	$\geq 1.00 \times 10^{15}$ ohm	$\geq 1.00 \times 10^{15}$ ohm	
Dielectric Constant	2.9	2.9	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.0	3.0	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	35.0 kV/mm	889 kV/in	
Dissipation Factor	0.0050	0.0050	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dissipation Factor	0.0090	0.0090	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	600 V	600 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China