

Ineos ABS NOVODUR® L3FR ABS, Injection Grade (discontinued **)

Category : Polymer , Thermoplastic , ABS Polymer , Acrylonitrile Butadiene Styrene (ABS), Unreinforced, Flame Retardant

Material Notes:

Injection molding grade, flame retardant, very easy flow. Contains no polyhalogenated diphenyls or diphenyl ethers. Applications: Television and computer housings. Information provided by the manufacturer. Novodur is produced by Styrolution (2014). This grade was discontinued prior to Styrolution's acquisition of the Novodur product line.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-ABS-NOVODUR-L3FR-ABS-Injection-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.18 g/cc	0.0426 lb/in ³	
Water Absorption	0.30 %	0.30 %	Saturation in water
Water Absorption at Saturation	0.30 %	0.30 %	
Melt Flow	48 g/10 min @Load 10.0 kg, Temperature 220 °C	48 g/10 min @Load 22.0 lb, Temperature 428 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	45.0 MPa	6530 psi	
Elongation at Yield	2.1 %	2.1 %	
Tensile Modulus	2.60 GPa	377 ksi	
Charpy Impact Unnotched	7.00 J/cm ²	33.3 ft-lb/in ²	
	0.250 J/cm ² @Temperature -30.0 °C	1.19 ft-lb/in ² @Temperature -22.0 °F	
Charpy Impact, Notched	0.500 J/cm ²	2.38 ft-lb/in ²	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	100 µm/m-°C @Temperature 20.0 °C	55.6 µin/in-°F @Temperature 68.0 °F	
Deflection Temperature at 0.46 MPa (66 psi)	90.0 °C	194 °F	
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	
Vicat Softening Point	89.0 °C	192 °F	

Thermal Properties	V-0 Metric	V-0 English	Comments
	@Thickness 1.60 mm	@Thickness 0.0630 in	
	V-0	V-0	
	@Thickness 3.20 mm	@Thickness 0.126 in	

Electrical Properties	Metric	English	Comments
Electrical Resistivity	1.00e+15 ohm-cm	1.00e+15 ohm-cm	
Surface Resistance	1.00e+15 ohm	1.00e+15 ohm	
Dielectric Constant	3.0	3.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	3.1	3.1	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	24.0 kV/mm	610 kV/in	
Dissipation Factor	0.0050	0.0050	
	@Frequency 100 Hz	@Frequency 100 Hz	
Comparative Tracking Index	0.0090	0.0090	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Comparative Tracking Index	450 V	450 V	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China