

## Ineos ABS Triax<sup>®</sup> 1315 GF ABS + Polyamide Blend (Conditioned)

Category : Polymer , Thermoplastic , ABS Polymer , Nylon

Material Notes:

Key Features: Contains Filler Suitable processing methods: Injection molding

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ineos-ABS-Triax-1315-GF-ABS-Polyamide-Blend-Conditioned.php](http://www.lookpolymers.com/polymer_ineos-ABS-Triax-1315-GF-ABS-Polyamide-Blend-Conditioned.php)

Physical Properties	Metric	English	Comments
Density	0.995 g/cc	0.0359 lb/in <sup>3</sup>	Melt
	1.17 g/cc	0.0423 lb/in <sup>3</sup>	(DAM)
Water Absorption	3.8 %	3.8 %	(from DAM)
Moisture Absorption at Equilibrium	1.3 %	1.3 %	23 <sup>°</sup> C/50% R.H. (from DAM)
Linear Mold Shrinkage, Flow	0.0040 cm/cm	0.0040 in/in	
Linear Mold Shrinkage, Transverse	0.0035 cm/cm	0.0035 in/in	
Melt Flow	3.0 g/10 min	3.0 g/10 min	
	@Load 5.00 kg, Temperature 260 <sup>°</sup> C	@Load 11.0 lb, Temperature 500 <sup>°</sup> F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Ultimate	70.0 MPa	10200 psi	
Elongation at Break	5.0 %	5.0 %	
Tensile Modulus	4.00 GPa	580 ksi	
Charpy Impact Unnotched	3.60 J/cm <sup>2</sup>	17.1 ft-lb/in <sup>2</sup>	
	3.60 J/cm <sup>2</sup> @Temperature -30.0 <sup>°</sup> C	17.1 ft-lb/in <sup>2</sup> @Temperature -22.0 <sup>°</sup> F	
Charpy Impact, Notched	1.00 J/cm <sup>2</sup>	4.76 ft-lb/in <sup>2</sup>	
	0.600 J/cm <sup>2</sup> @Temperature -30.0 <sup>°</sup> C	2.86 ft-lb/in <sup>2</sup> @Temperature -22.0 <sup>°</sup> F	

Thermal Properties	Metric	English	Comments
CTE, linear, Parallel to Flow	40.0 $\mu$ m/m- <sup>°</sup> C	22.2 $\mu$ in/in- <sup>°</sup> F	
			DAM

Thermal Properties	@Temperature 20.0 Metric °C	@Temperature 68.0 °F English °F	Comments
CTE, linear, Transverse to Flow	120 $\mu\text{m}/\text{m}\cdot\text{Å}^\circ\text{C}$ @Temperature 20.0 Å°C	66.7 $\mu\text{in}/\text{in}\cdot\text{Å}^\circ\text{F}$ @Temperature 68.0 Å°F	DAM
Specific Heat Capacity	1.94 J/g-Å°C	0.464 BTU/lb-Å°F	Melt
Thermal Conductivity	0.155 W/m-K	1.08 BTU-in/hr-ftÅ²- Å°F	Melt
Deflection Temperature at 1.8 MPa (264 psi)	95.0 Å°C	203 Å°F	(from DAM)
Vicat Softening Point	112 Å°C	234 Å°F	50Å°C/h 50N (from DAM)

Electrical Properties	Metric	English	Comments
Volume Resistivity	1.00e+10 ohm-cm	1.00e+10 ohm-cm	
Dielectric Constant	4.0	4.0	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	7.9	7.9	
	@Frequency 100 Hz	@Frequency 100 Hz	
Dielectric Strength	36.0 kV/mm	914 kV/in	
Dissipation Factor	0.070	0.070	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dissipation Factor	0.11	0.11	
	@Frequency 100 Hz	@Frequency 100 Hz	

Processing Properties	Metric	English	Comments
Melt Temperature	260 Å°C	500 Å°F	Injection Molding
Mold Temperature	80.0 Å°C	176 Å°F	Injection Molding
Ejection Temperature	105 Å°C	221 Å°F	
Injection Velocity	40.0 mm/sec	1.57 in/sec	

Descriptive Properties	Value	Comments
Effective thermal diffusivity	0.801E-7 mÅ²/s	Melt

Contact Songhan Plastic Technology Co.,Ltd.

**Website : [www.lookpolymers.com](http://www.lookpolymers.com)**

**Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)**

**Tel : +86 021-51131842**

**Mobile : +86 13061808058**

**Skype : lookpolymers**

**Address : United North Road 215,Fengxian District, Shanghai City,China**