

Ineos H13G-00 Polypropylene Homopolymer (discontinued **)

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

Formerly Amoco® 7444. Suggested fabrication methods: Injection molding
 Features: General purpose
 Typical applications: Rigid packaging, Medical components
 Complies with FDA specification, Title 21, CFR 177.1520.
 Typical property data below from injection molded samples. The polypropylene and polyethylene products of BP Amoco have been moved to the Innovene Division in 2005.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-H13G-00-Polypropylene-Homopolymer-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	0.886 - 0.926 g/cc	0.0320 - 0.0335 lb/in ³	ASTM D1505
Water Absorption	<= 0.010 %	<= 0.010 %	24 hours; ASTM D570
Linear Mold Shrinkage	0.010 - 0.025 cm/cm	0.010 - 0.025 in/in	ASTM D955
Melt Flow	13.5 g/10 min @Load 2.16 kg, Temperature 230 °C	13.5 g/10 min @Load 4.76 lb, Temperature 446 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	79 - 108	79 - 108	Normal range for injection molding resins; ASTM D785
Tensile Strength, Yield	35.0 MPa	5080 psi	ASTM D638
Elongation at Break	>= 500 %	>= 500 %	ASTM D638
Elongation at Yield	10 %	10 %	ASTM D638
Flexural Modulus	1.48 GPa	215 ksi	ASTM D790A
Izod Impact, Notched	0.200 - 0.300 J/cm @Diameter 3.17 mm	0.375 - 0.562 ft-lb/in @Diameter 0.125 in	bar

Thermal Properties	Metric	English	Comments
Maximum Service Temperature, Air	65.0 °C	149 °F	UL Relative Thermal Index
Deflection Temperature at 0.46 MPa (66 psi)	104 °C	219 °F	ASTM D648
Flammability, UL94	HB	HB	

Descriptive Properties	Value	Comments
------------------------	-------	----------

Process Injection

Descriptive Properties	Value	Comments
------------------------	-------	----------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China