

Ineos H35G-00 Polypropylene Homopolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene, Molded

Material Notes:

This is a general purpose homopolymer for injection molding applications. This material meets the requirements of the U.S. Food and Drug Administration as specified in 21 CFR 177.1520. Applications Consumer products Housewares Rigid packaging Fiber Extrusion coating Benefits Easy moldability Fast cycles at low processing temperatures Information provided by Ineos Olefins & Polymers USA

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-H35G-00-Polypropylene-Homopolymer.php

Physical Properties	Metric	English	Comments
Melt Flow	35 g/10 min	35 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 °C	@Load 4.76 lb, Temperature 446 °F	

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	34.5 MPa	5000 psi	ASTM D638
	@Temperature 23.0 °C	@Temperature 73.4 °F	
Elongation at Break	30 %	30 %	ASTM D638
Elongation at Yield	8.0 %	8.0 %	ASTM D638
Flexural Modulus	1.38 GPa	200 ksi	ASTM D790A
	@Temperature 23.0 °C	@Temperature 73.4 °F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	110 °C	230 °F	ASTM D648

Descriptive Properties	Value	Comments
Process	Injection Molding	
Region	Mexico	Bamberger Polymers Distribution
	US & Canada	Bamberger Polymers Distribution

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China