

Ineos Nova 2110 General Purpose Crystal Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Transparent Grade

Material Notes:

Moderately high heat resistance, Good balance of strength and ease of processing, USP Class VI Applications: Foam extrusion, Biaxially oriented sheet, Thermoformed drinkware, Molded packaging Exposure to gamma radiation in the 2.02-6.06 megarad range has no significant effect on the physical and optical properties of the material. Properties were determined on injection molded specimens at 23°C and 50% R.H. unless otherwise specified. Information provided by NOVA Chemicals. INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-Nova-2110-General-Purpose-Crystal-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in ³	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	3.4 g/10 min	3.4 g/10 min	Condition G

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	75	75	
Tensile Strength, Yield	43.0 MPa	6240 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Modulus of Elasticity	3.172 GPa	460.1 ksi	ASTM D638
Flexural Yield Strength	83.0 MPa	12000 psi	ASTM D790
Flexural Modulus	3.448 GPa	500.1 ksi	ASTM D790
Izod Impact, Notched	0.200 J/cm @Diameter 3.17 mm	0.375 ft-lb/in @Diameter 0.125 in	bar, 0.010" notch radius; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	91.0 °C	196 °F	ASTM D648
Vicat Softening Point	96.0 °C	205 °F	ASTM D1525

Optical Properties	Metric	English	Comments
Refractive Index	1.59 @Wavelength 589.3 nm	1.59 @Wavelength 589.3 nm	sodium D line

Optical Properties	Metric	English	Comments
Transmission, Visible	88 - 90 %	88 - 90 %	in avg. at 550 mm

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.59	2.59	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	19.7 kV/mm	500 kV/in	
	@Thickness 3.17 mm	@Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 274 °C	374 - 525 °F	
Mold Temperature	38.0 - 82.0 °C	100 - 180 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China