

Ineos Nova 5190 High Impact Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Impact Modified

Material Notes:

Good balance of toughness and rigidity, Superior gloss, USP Class VI Applications: Refrigeration, Appliances, High gloss applications Properties were determined on injection molded specimens at 23°C and 50% R.H. unless otherwise specified. Information provided by NOVA Chemicals. INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Ineos-Nova-5190-High-Impact-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in³	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	5.5 g/10 min	5.5 g/10 min	Condition G

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	32.0 MPa	4640 psi	ASTM D638
Elongation at Break	30 %	30 %	ASTM D638
Modulus of Elasticity	2.48 GPa	360 ksi	ASTM D638
Flexural Yield Strength	43.0 MPa	6240 psi	ASTM D790
Flexural Modulus	2.206 GPa	320.0 ksi	ASTM D790
Izod Impact, Notched	0.860 J/cm @Diameter 3.17 mm	1.61 ft-lb/in @Diameter 0.125 in	bar, 0.010" notch radius; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	88.0 °C	190 °F	ASTM D648
Vicat Softening Point	103 °C	217 °F	ASTM D1525
Flammability, UL94	HB	HB	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.51 @Frequency 1e+6 Hz	2.51 @Frequency 1e+6 Hz	
	15.7 kV/mm	400 kV/in	

Dielectric Strength Electrical Properties	Metric @ Thickness 3.17 mm	English @ Thickness 0.125 in	Comments
--	-------------------------------	---------------------------------	----------

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 274 °C	374 - 525 °F	
Mold Temperature	38.0 - 82.0 °C	100 - 180 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com
Email : sales@lookpolymers.com
Tel : +86 021-51131842
Mobile : +86 13061808058
Skype : lookpolymers
Address : United North Road 215,Fengxian District, Shanghai City,China