

## Ineos Nova 5810 High Impact Polystyrene (discontinued \*\*)

Category: Polymer, Thermoplastic, Polystyrene (PS), Polystyrene, Impact Modified

## **Material Notes:**

Balance of toughness and rigidity, Good gloss, USP Class VIApplications: Thermoformed and molded packaging, Drink cups and lids, Structural foam, Custom sheetProperties were determined on injection molded specimens at 23°C and 50% R.H. unless otherwise specified.Information provided by NOVA Chemicals.INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

## Order this product through the following link:

http://www.lookpolymers.com/polymer\_Ineos-Nova-5810-High-Impact-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.04 g/cc	0.0376 lb/in³	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	3.5 g/10 min	3.5 g/10 min	Condition G

Mechanical Properties	Metric	English	Comments	
Tensile Strength, Yield	28.0 MPa	4060 psi	ASTM D638	
Elongation at Break	30 %	30 %	ASTM D638	
Flexural Yield Strength	36.0 MPa	5220 psi	ASTM D790	
Flexural Modulus	1.793 GPa	260.1 ksi	ASTM D790	
Izod Impact, Notched	1.23 J/cm	2.30 ft-lb/in	bar, 0.010" notch radius; ASTM D256	
	@Diameter 3.17 mm	@Diameter 0.125 in		

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	85.0 °C	185 °F	ASTM D648
Vicat Softening Point	102 °C	216 °F	ASTM D1525
Flammability, UL94	НВ	НВ	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.51	2.51	
	@Frequency 1e+6 Hz	@Frequency 1e+6 Hz	
Dielectric Strength	15.7 kV/mm	400 kV/in	
	@Thickness 3.17 mm	@Thickness 0.125 in	



Electrical Properties Processing Properties	Metric Metric	English English	Comments Comments	
Melt Temperature	190 - 274 °C	374 - 525 °F		
Mold Temperature	38.0 - 82.0 °C	100 - 180 °F		

## **Contact Songhan Plastic Technology Co.,Ltd.**

Website: www.lookpolymers.com Email: sales@lookpolymers.com

Tel: +86 021-51131842 Mobile: +86 13061808058

Skype: lookpolymers

Address: United North Road 215, Fengxian District, Shanghai City, China