

Ineos Nova 602 Crystal Polystyrene GP Grade (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS) , Polystyrene, Transparent Grade

Material Notes:

Broad, medium melt flow range, Broad Vicat range Applications: Any; Injection Molding and Extrusion Properties were determined on injection molded specimens at 23°C and 50% R.H. unless otherwise specified. Information provided by NOVA Chemicals. INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-Nova-602-Crystal-Polystyrene-GP-Grade-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Density	1.06 g/cc	0.0383 lb/in ³	ISO 1183A
Melt Flow	5.0 - 10 g/10 min @Load 5.00 kg, Temperature 200 °C	5.0 - 10 g/10 min @Load 11.0 lb, Temperature 392 °F	ISO 1133

Mechanical Properties	Metric	English	Comments
Izod Impact, Notched	0.200 J/cm @Diameter 3.17 mm	0.375 ft-lb/in @Diameter 0.125 in	bar, 0.010" notch radius; ISO 180

Thermal Properties	Metric	English	Comments
Vicat Softening Point	88.0 - 99.0 °C	190 - 210 °F	ISO 306A

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.59 @Frequency 1e+6 Hz	2.59 @Frequency 1e+6 Hz	
Dielectric Strength	19.7 kV/mm @Thickness 3.17 mm	500 kV/in @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 274 °C	374 - 525 °F	
Mold Temperature	10.0 - 60.0 °C	50.0 - 140 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China