

Ineos Nova PS 2520 Crystal Polystyrene (discontinued **)

Category : Polymer , Thermoplastic , Polystyrene (PS)

Material Notes:

Information provided by Nova Chemicals/INEOS NOVA began October 1 2007 as an expansion of the 50:50 joint venture between NOVA Chemicals and INEOS to include North American assets.

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-Nova-PS-2520-Crystal-Polystyrene-nbspdiscontinued-.php

Physical Properties	Metric	English	Comments
Specific Gravity	1.04 g/cc	1.04 g/cc	ASTM D792
Linear Mold Shrinkage	0.0040 - 0.0070 cm/cm	0.0040 - 0.0070 in/in	ASTM D955
Melt Flow	7.5 g/10 min @Load 5.00 kg, Temperature 200 °C	7.5 g/10 min @Load 11.0 lb, Temperature 392 °F	old Condition G; ASTM D1238

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell M	62	62	ASTM D785
Tensile Strength at Break	47.0 MPa	6820 psi	ASTM D638
Elongation at Break	2.0 %	2.0 %	ASTM D638
Tensile Modulus	3.41 GPa	495 ksi	ASTM D638
Flexural Strength	96.0 MPa	13900 psi	at <5%; ASTM D790
Flexural Modulus	3.30 GPa	479 ksi	ASTM D790
Izod Impact, Notched	0.210 J/cm @Diameter 3.17 mm	0.393 ft-lb/in @Diameter 0.125 in	bar; ASTM D256

Thermal Properties	Metric	English	Comments
Deflection Temperature at 1.8 MPa (264 psi)	100 °C	212 °F	annealed; ASTM D648
Vicat Softening Point	91.0 °C	196 °F	Rate B; ASTM D1525

Optical Properties	Metric	English	Comments
Refractive Index	1.59 - 1.60 @Wavelength 589.3 nm	1.59 - 1.60 @Wavelength 589.3 nm	Sodium D Line
Optical Density	0.046	0.046	400 mm- 700 mm average

Optical Properties	Metric	English	Comments
Transmission, Visible	@Wavelength 550 nm	@Wavelength 550 nm	

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.59 @Frequency 1e+6 Hz	2.59 @Frequency 1e+6 Hz	
Dielectric Strength	19.7 kV/mm @Thickness 3.17 mm	500 kV/in @Thickness 0.125 in	

Processing Properties	Metric	English	Comments
Melt Temperature	190 - 274 °C	374 - 525 °F	
Mold Temperature	38.0 - 82.0 °C	100 - 180 °F	

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China