

Ineos T20N-00 Polypropylene Impact Copolymer

Category : Polymer , Thermoplastic , Polypropylene (PP) , Polypropylene Copolymer , Polypropylene, Impact Modified; Molded/Extruded

Material Notes:

This is a special high melt flow, nucleated, high impact copolymer polypropylene for injection molding applications. It offers excellent impact resistance and a high flexural modulus. Applications Consumer products Industrial applications Benefits High impact resistance High flexural modulus Information provided by Ineos Olefins & Polymers USA

Order this product through the following link:

http://www.lookpolymers.com/polymer_ineos-T20N-00-Polypropylene-Impact-Copolymer.php

Physical Properties	Metric	English	Comments
Melt Flow	20 g/10 min	20 g/10 min	ASTM D1238
	@Load 2.16 kg, Temperature 230 Â°C	@Load 4.76 lb, Temperature 446 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Rockwell R	49	49	ASTM D785
Tensile Strength, Yield	20.0 MPa	2900 psi	ASTM D638
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Elongation at Break	80 %	80 %	ASTM D638
Flexural Modulus	1.17 GPa	170 ksi	D790B
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	
Izod Impact, Notched	0.908 J/cm	1.70 ft-lb/in	1/8" notched bar; ASTM D256
	@Temperature -20.0 Â°C	@Temperature -4.00 Â°F	
	NB	NB	1/8" notched bar; ASTM D256
	@Temperature 23.0 Â°C	@Temperature 73.4 Â°F	

Thermal Properties	Metric	English	Comments
Deflection Temperature at 0.46 MPa (66 psi)	102 Â°C	215 Â°F	ASTM D648

Descriptive Properties	Value	Comments
Multi-axial Instrumented Impact (10.9 ft/s)	13.2	negative 20Â°C, energy at max load, D3763
	ductile	failure mode, D3763

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China