

Intercontinental Polymers 1180 Bicomponent PP/PET Fiber Type - 3 Denier X 1.5 Inches

Category : Polymer , Thermoplastic , Polyester, TP , Polyethylene Terephthalate (PET) , Polypropylene (PP)

Material Notes:

40/60 PP Sheath/PET Core. Luster: Semi-Dull. Finish: Hydrophilic. Applications of bicomponent polyester fiber: Absorbent products, hygiene products, non-wovens, filtration, sliver knit, microdenier fabrics, synthetic suede fabrics and wipes, automobile headliners. Information provided by Intercontinental Polymers.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Intercontinental-Polymers-1180-Bicomponent-PPPET-Fiber-Type-3-Denier-X-15-Inches.php

Mechanical Properties	Metric	English	Comments
Elongation at Break	23 - 53 %	23 - 53 %	LFL-09
Tenacity	0.282 - 0.353 N/tex	3.20 - 4.00 g/denier	LFL-09

Thermal Properties	Metric	English	Comments
Melting Point	162 - 168 Â°C	324 - 334 Â°F	Sheath Melt Point; LCL-PR29
Shrinkage	0.00 - 6.0 %	0.00 - 6.0 %	Hot Air Shrinkage; LFL-07

Descriptive Properties	Value	Comments
Crimp/Inch	12 - 18	LFL-03
Finish	0.2 - 0.8%	LCL-PR39

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China