

## Ipiranga Petrochem GF 4950 HDPE

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Blow Molding Grade

### Material Notes:

IPQ produces High Density Polyethylene (HDPE) for use by different segments of the plastics molding industry in several processes, including blow molding, extrusion and injection molding. To produce HDPE, IPQ employs Hoechst/Hostalen technology through the following steps: the ethene supplied by COPELUL is processed by Ipiranga Petroquímica in reactors to produce powdered polyethylene. The polyethylene then receives additives and is homogenized with stabilizers and taken to extruding presses where it is granulated and is ready for marketing. An integrated and computerized system controls the production, from the initial processing stages to end-product testing for later commercialization. Applications: big bottles for chemical products containers for detergent surfactants cosmetics shoe mold small automotive reservoirs

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_ipiranga-Petrochem-GF-4950-HDPE.php](http://www.lookpolymers.com/polymer_ipiranga-Petrochem-GF-4950-HDPE.php)

Physical Properties	Metric	English	Comments
Density	0.953 - 0.959 g/cc	0.0344 - 0.0346 lb/in <sup>3</sup>	ASTM D792-98
Melt Flow	0.26 - 0.42 g/10 min @Load 2.16 kg, Temperature 190 °C	0.26 - 0.42 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238-00

Mechanical Properties	Metric	English	Comments
Tensile Strength, Yield	28.0 MPa	4060 psi	ASTM D638-02
Elongation at Yield	7.8 %	7.8 %	ASTM D638-02
Flexural Modulus	1.04 GPa	151 ksi	2% secant; ASTM D790-02
Izod Impact, Notched	1.40 J/cm	2.62 ft-lb/in	ASTM D256-03

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215, Fengxian District, Shanghai City, China