

Ipiranga Petrochem LBH 0117 LLDP

Category : Polymer , Film , Thermoplastic , Polyethylene (PE) , LLDPE , Linear Low Density Polyethylene (LLDPE)/Hexene, Film Grade

Material Notes:

IPQ produces Linear Low Density Polyethylene (LLDPE) for use by plastics molding industry segments that employ extrusion processes in the manufacturing of films destined for producing bobbins and bags. IPQ employs Spherilene technology from Montell/Italy in the production of LLDPE. The raw materials, which are supplied by COPESUL, are pre-treated and fed into gas-phase reactors, where linear low density polyethylene globe-shaped grains are obtained. These grains are sent to the extrusion site, where stabilizers are added to them. The grains are turned into pellets by an extruding press. Next, they are sent to storage silos, and then to the packaging site. This technology uses state-of-the-art techniques to control the entire production process, thus ensuring the quality of the products that are marketed.

Applications: stretch blow film for manual and automatic application

Order this product through the following link:

http://www.lookpolymers.com/polymer_ipiranga-Petrochem-LBH-0117-LLDP.php

Physical Properties	Metric	English	Comments
Density	0.917 g/cc	0.0331 lb/in ³	ASTM D1505-98
Melt Flow	0.60 - 0.90 g/10 min @Load 2.16 kg, Temperature 190 °C	0.60 - 0.90 g/10 min @Load 4.76 lb, Temperature 374 °F	ASTM D1238-00

Mechanical Properties	Metric	English	Comments
Film Tensile Strength at Yield, MD	12.0 MPa	1740 psi	ASTM D882-02
Film Tensile Strength at Yield, TD	12.0 MPa	1740 psi	ASTM D882-02
Film Elongation at Break, MD	780 %	780 %	ASTM D882-02
Film Elongation at Break, TD	860 %	860 %	ASTM D882-02
Film Elongation at Yield, MD	23 %	23 %	ASTM D882-02
Film Elongation at Yield, TD	12 %	12 %	ASTM D882-02
Coefficient of Friction	0.80	0.80	ASTM D1894-99
Dart Drop Test	250 g	0.551 lb	ASTM D1709-98
Film Tensile Strength at Break, MD	45.0 MPa	6530 psi	ASTM D882-02
Film Tensile Strength at Break, TD	37.0 MPa	5370 psi	ASTM D882-02

Optical Properties	Metric	English	Comments
Haze	25 %	25 %	ASTM D1003A-00

Gloss Optical Properties	30 % Metric	30 % English	ASTM D785-03 Comments
-----------------------------	----------------	-----------------	--------------------------

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China