

Iran Petrochemical (PCC) EX 2 S HF 7750 M2 High Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , HDPE, Fiber Grade

Material Notes:

EX2S is a high density polyethylene with 1-Butene as co monomer. It is medium molar mass, low density grade with a narrow molar mass distribution, high rigidity, good tear strength. Applications: monofilaments, ropes, yarns, netting geotextiles & cavil engineering. Information provided by Iran Petrochemical Commercial Co.

Order this product through the following link:

http://www.lookpolymers.com/polymer_Iran-Petrochemical-PCC-EX-2-S-HF-7750-M2-High-Density-Polyethylene.php

Physical Properties	Metric	English	Comments
Density	0.956 g/cc	0.0345 lb/in ³	ISO 1183
Melt Flow	3.3 g/10 min	3.3 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 190 Â°C	@Load 11.0 lb, Temperature 374 Â°F	
	33 g/10 min	33 g/10 min	ISO 1133
	@Load 21.6 kg, Temperature 190 Â°C	@Load 47.6 lb, Temperature 374 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	62	62	ISO 868
Tensile Stress	31.0 MPa	4500 psi	at Break; ISO 527
Tensile Strength, Yield	27.0 MPa	3920 psi	ISO 527
Elongation at Break	>= 1000 %	>= 1000 %	ISO 527
Elongation at Yield	10 %	10 %	ISO 527
Tensile Modulus	1.20 GPa	174 ksi	ISO 527
Charpy Impact, Notched	2.30 J/cm ²	10.9 ft-lb/in ²	ISO 179/1eA

Thermal Properties	Metric	English	Comments
Softening Point	80.0 Â°C	176 Â°F	ISO 306
Brittleness Temperature	>= -80.0 Â°C	>= -112 Â°F	ASTM D746-72

Processing Properties	Metric	English	Comments
Melt Temperature	220 - 270 Â°C	428 - 518 Â°F	

Descriptive Properties	Value	Comments
Flexural Creep Modulus (MPa)	1350	4 point, 1 min; DIN 19537-2

Contact Songhan Plastic Technology Co.,Ltd.

Website : www.lookpolymers.com

Email : sales@lookpolymers.com

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China