

## Iran Petrochemical (PCC) EX 6HT HM 9455 HT High Density Polyethylene

Category : Polymer , Thermoplastic , Polyethylene (PE) , HDPE , High Density Polyethylene (HDPE), Extruded , High Density Polyethylene (HDPE), Film Grade

### Material Notes:

EX 6HT is a high density polyethylene with 1-Butene as co monomer. It has good toughness, low gel level, good tear strength, high tenacity. Applications: film extrusion, blending partner, refuse bags, carrier bags, heavy duty packing. Information provided by Iran Petrochemical Commercial Co.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Iran-Petrochemical-PCC-EX-6HT-HM-9455-HT-High-Density-Polyethylene.php](http://www.lookpolymers.com/polymer_Iran-Petrochemical-PCC-EX-6HT-HM-9455-HT-High-Density-Polyethylene.php)

Physical Properties	Metric	English	Comments
Density	0.944 g/cc	0.0341 lb/in <sup>3</sup>	ISO 1183
Melt Flow	0.18 g/10 min	0.18 g/10 min	ISO 1133
	@Load 5.00 kg, Temperature 190 Â°C	@Load 11.0 lb, Temperature 374 Â°F	
	5.4 g/10 min	5.4 g/10 min	ISO 1133
	@Load 21.6 kg, Temperature 190 Â°C	@Load 47.6 lb, Temperature 374 Â°F	

Mechanical Properties	Metric	English	Comments
Hardness, Shore D	58	58	ISO 868
Tensile Stress	36.0 MPa	5220 psi	at Break; ISO 527
Tensile Strength, Yield	21.0 MPa	3050 psi	ISO 527
Film Elongation at Break, MD	<= 450 %	<= 450 %	ISO 527
Film Elongation at Break, TD	<= 500 %	<= 500 %	ISO 527
Elmendorf Tear Strength MD	20.4 g	20.4 g	ISO 6383-2
Elmendorf Tear Strength TD	40.8 g	40.8 g	ISO 6383-2
Dart Drop Test	240 g	0.529 lb	ASTM D1709
Film Tensile Strength at Break, MD	<= 45.0 MPa	<= 6530 psi	ISO 527
Film Tensile Strength at Break, TD	<= 40.0 MPa	<= 5800 psi	ISO 527

Thermal Properties	Metric	English	Comments
Softening Point	73.0 Â°C	163 Â°F	ISO 306
Brittleness Temperature	>= -80.0 Â°C	>= -112 Â°F	ASTM D746-72

Thermal Properties	Metric	English	Comments
Processing Properties	Metric	English	Comments
Melt Temperature	200 - 230 Å°C	392 - 446 Å°F	

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China