

## Iran Petrochemical (PCC) PC 5970 Polycarbonate

Category : Polymer , Thermoplastic , Polycarbonate (PC)

### Material Notes:

Suitable for injection molding Information provided by Iran Petrochemical Commercial Co.

Order this product through the following link:

[http://www.lookpolymers.com/polymer\\_Iran-Petrochemical-PCC-PC-5970-Polycarbonate.php](http://www.lookpolymers.com/polymer_Iran-Petrochemical-PCC-PC-5970-Polycarbonate.php)

Physical Properties	Metric	English	Comments
Density	1.20 g/cc	0.0434 lb/in <sup>3</sup>	ASTM D792
Melt Flow	59.1 - 70 g/10 min @Load 1.20 kg, Temperature 300 °C	59.1 - 70 g/10 min @Load 2.65 lb, Temperature 572 °F	ASTM D1238

Mechanical Properties	Metric	English	Comments
Ball Indentation Hardness	>= 103 MPa	>= 14900 psi	DIN 53456
Tensile Stress	55.0 - 70.0 MPa	7980 - 10200 psi	ASTM D638
Tensile Strength, Yield	>= 60.0 MPa	>= 8700 psi	ASTM D638
Elongation at Break	>= 50 %	>= 50 %	ASTM D638
Modulus of Elasticity	2.20 - 2.40 GPa	319 - 348 ksi	ASTM D638

Thermal Properties	Metric	English	Comments
Vicat Softening Point	140 - 150 °C	284 - 302 °F	50 N, 50°C/h; ASTM D1525

Optical Properties	Metric	English	Comments
Transmission, Visible	>= 80 % @Thickness 2.00 mm	>= 80 % @Thickness 0.0787 in	ASTM D1003

Electrical Properties	Metric	English	Comments
Dielectric Constant	2.8 - 3.1 @Frequency 1.00e+6 Hz	2.8 - 3.1 @Frequency 1.00e+6 Hz	ASTM D150
Dielectric Strength	>= 20.0 kV/mm @Frequency 50.0 Hz	>= 508 kV/in @Frequency 50.0 Hz	ASTM D149
	0.00080 - 0.0010	0.00080 - 0.0010	

Dielectric Loss Index Electrical Properties	@Frequency 5.00e+7 Metric Hz	@Frequency 5.00e+7 English Hz	ASTM D150 Comments
	0.0080 - 0.011	0.0080 - 0.011	
	@Frequency 1.00e+6 Hz	@Frequency 1.00e+6 Hz	ASTM D150

Descriptive Properties	Value	Comments
Solvent Content, ppm	< 500	GC

## Contact Songhan Plastic Technology Co.,Ltd.

Website : [www.lookpolymers.com](http://www.lookpolymers.com)

Email : [sales@lookpolymers.com](mailto:sales@lookpolymers.com)

Tel : +86 021-51131842

Mobile : +86 13061808058

Skype : lookpolymers

Address : United North Road 215,Fengxian District, Shanghai City,China